

The FEA Code of LASCAD

Konrad Altmann

LAS-CAD GmbH

Heat removal and thermal lensing constitute key problems for the design of laser cavities for solid-state lasers (SSL, DPSSL etc.). To compute thermal effects in laser crystals LASCAD uses a Finite Element code specifically developed to meet the demands of laser simulation.

The thermal analysis is carried through in three steps:

- Determination of heat load distribution,
- Solution of the 3-D differential equations of heat conduction,
- Solution of the differential equation of structural deformation.

Differential Equation of Heat Conduction

Differential equations of conduction of heat

$$- \operatorname{div} [\kappa(T) \nabla(T)] = Q(x, y, z)$$

κ coefficient of thermal conductivity

T temperature

Q heat load distribution

$$T = T_D$$

Dirichlet boundary condition

Surface kept on constant temperature

Boundary condition for fluid cooling

$$-k \left(\frac{\partial T}{\partial n_x}, \frac{\partial T}{\partial n_y}, \frac{\partial T}{\partial n_z} \right) = h_f (T_s - T)$$

h_f film coefficient

T_s surface temperature

Differential Equations of Structural Deformation

Strain-stress relation

$$(\varepsilon_{ij}) = (\alpha_x, \alpha_y, \alpha_z)(T - T_0) + \frac{1}{E} C^{-1}(\sigma_{ij})$$

$$0 = \text{div}(\sigma_{ij})$$

$\sigma_{i,j}$ stress tensor

α_i coefficient of thermal expansion


E elastic modulus


$$\varepsilon_{ij} = \frac{1}{2} \left(\frac{\partial u_i}{\partial x_j} + \frac{\partial u_j}{\partial x_i} \right)$$

$\varepsilon_{i,j}$ strain tensor,
 u_i displacement

To solve these differential equations, a finite element discretization is applied on a semi-unstructured grid.

This terminus means that the grid has regular and equidistant structure inside the crystal which is fitted irregularly to the boundaries of the body. See for instance the case of a rod





Semi-unstructured grid in case of a rod

Semi-unstructured meshing has a series of useful properties:

- The structured grid inside the body allows for efficient use of the results with optical codes, for instance easy interpolation,
- Meshing can be carried through automatically,
- The grids can be stretched in x-, y-, and z-direction,
- High accuracy can be achieved by the use of small mesh size,
- The superconvergence of the gradient inside the domain leads to an accurate approximation of stresses.


Computation of Heat Load Distribution

Computation of heat load can be carried through in two ways:

- 1) Use of analytical approximations
- 2) Numerical computation by the use of ray tracing codes. LASCAD does not have its own ray tracing code, but has interfaces to the well known and reliable codes ZEMAX and TracePro.

For the analytical approximation of the heat load supergaussian functions are used.

As an example I am discussing the case of an end pumped rod with a pump beam being focussed from the left end into the rod.



In this case the absorbed pump power density can be described as follows

$$Q(x, y, z) = \frac{\alpha \beta P}{C_x C_y w_x w_y} \exp \left[-2 \left| \frac{x}{w_x} \right|^{SGX} - 2 \left| \frac{y}{w_y} \right|^{SGY} - \alpha z \right]$$

P incident pump power

α absorption coefficient

z distance from entrance plane

β heat efficiency

C_x, C_y normalization constants

SGX, SGY supergaussian exponents

SG=2 common gaussian, SG ∞ tophat

w_x, w_y local spot sizes

Local spot sizes w_x and w_y are given by

$$w_x = \sqrt{[w_{0x}^2 + ((z - f_x)\theta_x)^2]}$$

and

$$w_y = \sqrt{[w_{0y}^2 + ((z - f_y)\theta_y)^2]}$$

θ divergence angle


f distance from entrance plane

The pump beam can be defined astigmatic, for instance common gaussian the x direction and tophat in y direction. Also pumping from both ends is possible.

With the above equations the heat load in end pumped crystals can be approximated very closely.

Similarly, side pumping of a cylindrical rod can be described by the use of analytical approximations as will be shown now.

Side Pumped Rod



In this case the propagation of the pump beam in a plane perpendicular to the crystal axis is described by the Gaussian algorithm. It is assumed that the transformation of the beam traversing the different cylindrical surfaces can be described by appropriate matrices. This issue is described in more detail in Tutorial No.2.

Two important parameters have to be adjusted to get the correct heat load

α **absorption coefficient** of the pump light

β **heat efficiency** of the laser material


By the use of the **absorption coefficient** the attenuation of the pump light can be described by the use of an exponential law

$$I(z) = I(z = 0) \exp(-\alpha z)$$


The absorption coefficient can be determined experimentally by measuring the transmission through a plate of the laser material.

Numerically the absorption coefficient can be determined by computing the overlap integral of the emission spectrum of the laser diode and the absorption spectrum of the laser material

$$I(z) = \int_{\lambda_1}^{\lambda_2} f_e(\lambda) \exp(-\alpha(\lambda) z) d\lambda$$



Absorption spectrum of 1 atomic % Nd:YAG



Emission spectra of high power laser diode P1202 of Coherent, Inc. for different values of diode current at constant temperature 20° C.

The **heat efficiency** β of the laser material, also called fractional thermal load, is the relative amount of the absorbed pump power density which is converted into heat load. The heat efficiency is defined by

$$\beta = \frac{P_{heat}}{P_{abs}},$$

where P_{abs} is the absorbed pump power and P_{heat} is the generated thermal load.

The **heat efficiency** β of the laser material depends on quantummechanical properties of the laser material and can determined by the following equation

$$\beta = 1 - \eta_p \left[(1 - \eta_l) \eta_r \frac{\lambda_p}{\lambda_f} + \eta_l \frac{\lambda_p}{\lambda_l} \right]$$

η_p pump efficiency (fraction of absorbed pump photons which contribute to the population of the upper laser level)

η_r efficiency of spontaneous emission

η_l efficiency of stimulated emission

λ_p pump wave length

λ_l wave length of lasing transition

λ_f averaged fluorescence wave length

Neglecting the difference between λ_l and λ_f in a rough approximation the above expression for the heat efficiency can be written as

$$\beta = 1 - \eta_p \frac{\lambda_p}{\lambda_l} (\eta_l + \eta_r (1 - \eta_l)).$$

This equation shows that the heat efficiency mainly is determined by the ratio λ_p/λ_l .

For important laser materials values for the heat efficiency can be found in the literature. For instance, for Nd:YAG the value 0.3 usually is found and delivers reliable results. This value has been checked in cooperation with German universities, and has been delivering very good agreement with measurements for the thermal lens in many cases.

Since for Yb:YAG the lower laser level is close to ground level the heat efficiency is smaller. A value of 0.11 turned out to deliver good agreement with measurements for the thermal lens.

As mentioned in the paper "introduction and overview.ppt" measurements carried through by the Solid-State Lasers and Application Team (ELSA) *Centre Université d'Orsay, France* delivered good agreement with LASCAD simulation.


Numerical Computation of Heat Load Distribution

Analytical approximations for the absorbed pump power density are not always sufficient. There are situations, for instance scattering surfaces of the crystal, where numerical computation by the use of a ray tracing code is necessary.


For this purpose LASCAD has interfaces to the ray tracing codes ZEMAX and TracePro.

Both programs can compute the absorbed pump power using a discretization of the crystal volume into a rectangular voxels. The pump power absorbed absorbed in each voxel is written to a 3D data set which can be used as input for LASCAD which is interpolating the data with respect to the grid used by the FEA code.


On the LASCAD CD-ROM the following example can be found for a flashlamp pumped rod analyzed by the use of ZEMAX.




After 3D interpolation the heat load shown below is obtained with LASCAD




Another interesting configuration has been analyzed by one of our customers by the use of TracePro. Here you can see a crystal rod which is embedded in a block of copper. The pump light is coming from a diode bar is entering through this slot.





Absorbed pump power density computed by the
use of TracePro

Interpolation is LASCAD delivers this plot




Computation of Stress Intensity

Since the individual components of the stress tensor do not deliver sufficient information concerning fracture problems, the stress intensity is being computed which is defined by

$$\sigma_I = \text{MAX} \left(\left| \sigma_1 - \sigma_2 \right|, \left| \sigma_2 - \sigma_3 \right|, \left| \sigma_3 - \sigma_1 \right| \right)$$

Here σ_1 , σ_2 und σ_3 are the components of the stress tensor with respect to the principal axis. The stress tensor is a useful parameter to control cracking limits.



Stress intensity in an end pumped rod